



Technical Specification

GBsuper pig. Blue

Product Name : GBsuper pig. blue
Chemical class : phethalocyanine

Physical Property

From : Free flowing powder
 Pigmentation : 55%
 Bulk density : 1.3
 PH : 8 to 8.5

Field of application : (for water based applications)

Useful for coloring following fields of application.

- Water based paints
- Water based inks
- Building and construction
- Leather
- Paper and pulp
- Detergents
- Artist's colors
- Textile printing
- How to make cement cube from GB super pig i.e. "Colored Concrete"?
- 5000 grams sand ,
- 5600 grams of gravel ,
- 1666 grams of cement
- 1.33 liters of water
- 22 grams GBsuper Pigment
- Quality and durability test applied to that cubes & the result is very good

Cairo head office: 9,square 1163,El Shaheed Fouad Thabet St.,El Wozara square Sheraton Heliopolis. Cairo-Egypt

Cairo Tel. : 00202222683983

Fax : 00202 22684663

Mobile : 002012 23109645 / 002012 28099699

E-mail : gbchem@gb-chem.net

E-mail : gammy.botros@link.net

Alex. Tel. : 00203 4819240

Fax : 00203 4817565

Mobile : 002012 21148181

E-mail : gbchemalex@gb-chem.net

E-mail : logistics@gb-chem.net

Product name: **GB**superpig. Blue

Reduction:

1- pigment Application

Printing Inks	: √
Gravure printing Inks	: √
Tin printing Inks	: √
Decorative Paints	: √
Automotive Paints	: √
Industrial Paints	: √
Polyethylene Plastic	: √
Polystyrene Plastics	: √
PVC Plastics	: √
Rubber	: √
Dry colours	: √
Paper	: √
Stationery / Artists Material	: √
Pigment Ptg. Emulsion Textiles	: √
Mass Colouration of viscose	: -
Detergents	: -

2- Legends Used

- √ Recommended for use
- × Not Recommended
- Some Rrestricted Use

3- Pigment Properties

Water	: 5
Specific Gravity	: 1.4
Oil Absorption (gm/100gms)	: 40
Hue	: Blue
Heat Resistance	: 180
Chemical Resistance	: CPC
5 % soda Ash	: 5
5 % Acid (HCl)	: 5
Linseed Oil	: 5
Oleic Acid	: 5
Plasticisers	: 5
Soap Gel Bleed	: 5

4- Fastness Properties

Light Fastness	
25 % shade	: 7-8
10 % shade	: 7-8
5 % shade	: 7-8
Solvent Fastness	
Mineral Turpentine	: 5
Cellosolve	: 4-5
Esters	: 5
Ethanol	: 5
Ketones	: 5
NC Solvents	: 4-5
Xylene	: 4-5