

Product name: GBsuper pig. Orange

Reduction:

1- pigment Application

Offset	: ✓
Gravure	: ✓
Flexo	: ✓
TPC Inks	: ✓
Emulsion Paint	: ✓
Air Drying Enamel	: ✓
Stoving Enamel	: ✓
N.C Lacquer	: ✓
O.B.D	: ✓
Distempers	: ✓
Plastics	: ✓
Leather Cloth	: ✓
Rubber	: ✓
Aqueous Emulsion	: ✓

2- Legends Used

- ✓ Recommended for use
- × Not Recommended
- Some Restricted Use

3- Pigment Properties

Specific Gravity	: 1.4
Oil Absorption (gm/100gms)	: 50
pH of 1 % extract	: 7
Reagents (Sacle:1 to 5)	
Water	: 5
5%HCl	: 5
5%NaOH	: 5
Lime	: 5
Solvents (Sacle:1 to 5)	
Ethanol	: 4
N-Butanol	: 4
N-Buty Acetate	: 3
M.E.K	: 2
Plasticizers (Sacle:1 to 5)	
White Spirit	: 4
Xylene	: 4
Mixed NC Solvents	: 4
Cellosolve	: 4

4- Fastness Properties

Light (1 to 8)	
Full strength	: 6
Reduction 1:10 Tio2	: 4
Heat (1 to 5)	
150° C (300 F) 20 min	: 4
180° C (355 F) 10 min	: 3
120° C (300 F) 30 min	: 2
N.C.Lacquer	: 4

Cairo head office: 9,square 1163,El Shaheed Fouad Thabet St.,El Wozara square Sheraton Heliopolis. Cairo-Egypt

Cairo Tel. : 00202222683983

Fax : 00202 22684663

Mobile : 002012 23109645 / 002012 28099699

E-mail : gbchem@gb-chem.net

E-mail : gammy.botros@link.net

Alex. Tel. : 00203 4819240

Fax : 00203 4817565

Mobile : 002012 21148181

E-mail : gbchemalex@gb-chem.net

E-mail : logistics@gb-chem.net